



SAFETY SIGNS PRODUCTS

EXS High Grade Fotoluminiserend

<u>Subject</u>	<u>Results</u>
Composition	Composite construction
Type of adhesive	Solvent acrylic
Overall thickness (mm)	1.52 mm
Tackloop (kg/25.4 mm)	2.88
Cohesion (mins/25°C)	4320
Adhesion to steel (kg/25.4 mm)	2.3
Temperature range	-100C - 800C
Maximum roll size	1220 mm x 100 m
Life (months)	10 to 24

Coefficient of friction data

	Dry surface test result	Wet surface test result
Coarse Resilient	102 TRL	47 TRL

Photoluminescent data

Time	Luminance mcd/m2	Test date
10 minutes	107	040-4-2014
60 minutes	32	04-04-2014

Photoluminescent tests performed bij Photo metric and Optical Testing Service, England

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.